

K.H.N. 1

86-11

(1)

Science Center
Rockwell International Corporation
1049 Camino Dos Rios
P.O. Box 1085
Thousand Oaks, California 91360



Rockwell
International

(805) 373-4545

AD-A220 233

① GROWTH OF TUNGSTEN BRONZE FAMILY CRYSTALS - L

March 18, 1986

In Reply Refer To: SC86-533

Naval Research Laboratory
4555 Overlook Avenue, S. W.
Washington, DC 20375

Attention: Dr. Philipp H. Klein
Code 6822

Subject: Quarterly Technical Report No. 2
For Period 12/01/85 through 02/28/86
Contract No. N00014-85-C-2443
SC5441.QTR

⑤ 12/85 - 2/86 : 3/86

In accordance with the requirements stated for Contract No.
N00014-85-C-2443, enclosed herewith is Quarterly Technical
Report No. 2 for the period 12/01/85 through 02/28/86.

② ROCKWELL INTERNATIONAL CORPORATION
Science Center

Ratnakar R. Neurgaonkar

Ratnakar R. Neurgaonkar
Manager
Ferroelectric Materials Department

RRN/mrw

enclosure

cc: Attached Distribution List

DISTRIBUTION STATEMENT A
Approved for public release
Distribution Unlimited

Technical Information covers 11 number(s) NONE
Abstracted: Date: _____

DTIC
ELECTE
APR 10 1990
S
CO D

ADVISORY GROUP
RECEIVED
MAR 24 1986
RECEIVED
ON ELECTRON DEVICES

④ QUARTERLY TECH.

③ N00014-85-C-2443

③

90

DISTRIBUTION FOR G. O. 5441

Dr. H. E. Bennett, Code 38101
Michelson Laboratory
Naval Weapons Center
China Lake, CA 93555

Dr. Paul Fletcher
Code 92
Naval Ocean Systems Center
San Diego, CA 92152

Dr. Joseph Friebele
Code 6570
Naval Research Laboratory
Washington, DC 20375-5000

Director
Defense Advanced Research Projects Agency
Attn: Program Management
1400 Wilson Blvd.
Arlington, VA 22209

Dr. Robert C. Pohanka
Code 431
Office of Naval Research
800 N. Quincy St.
Arlington, VA 22216

Dr. Edward Sharp
Code DELNV-R
Night Vision & Electro-Optics Laboratory
Ft. Belvoir, VA 22060

Dr. W. K. Burns
Code 6570
Naval Research Laboratory
Washington, DC 20375-5000

Mr. William Woody
AFWAL/MLPJ
Wright Patterson Air Force Base, OH 45433

Advisory Group on Electron Devices
201 Varick Street
New York, NY 10014

Capt. Kevin Malloy
AFOSR/NE
Bolling Air Force Base, DC 20332

DCASMA/Van Nuys
Attention: CAO Terminal/GVW
6230 Van Nuys Blvd.
Van Nuys, CA 91401-2713

Accession For	
NTIS CRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By <i>AD-A 211154</i>	
Distribution /	
Availability Codes	
Dist	Avail and/or Special
<i>A-1</i>	





Rockwell International
Science Center

MARCH 1986

SC5441.QTR

GROWTH OF TUNGSTEN BRONZE
FAMILY CRYSTALS

QUARTERLY TECHNICAL REPORT NO. 2
THE PERIOD 12/01/85 THROUGH 02/28/86

DARPA ORDER NO.:	4540
NAME OF CONTRACTOR:	Rockwell International Corporation
EFFECTIVE DATE OF CONTRACT:	05/02/85
CONTRACT EXPIRATION DATE:	01/30/88
AMOUNT OF CONTRACT DOLLARS:	\$1,245,307
CONTRACT NO.:	N00014-85-C-2443
PRINCIPAL INVESTIGATOR:	Dr. R. R. Neurgaonkar (805) 373-4109

Professor L. E. Cross
Pennsylvania State University
(814) 865-1181

Sponsored By:

DEFENSE ADVANCED RESEARCH PROJECTS AGENCY (DoD)
DARPA ORDER NO. 4540

A. OBJECTIVE

The objective of the present work is to develop suitable quality and size $\text{Sr}_{0.6}\text{Ba}_{0.4}\text{Nb}_2\text{O}_6$ (SBN) single crystals or thin films that can be used in optical device studies. The second objective of this work is to develop a phenomenological model to explain the correlation between the ferroelectric and optical properties and thereby possibly control and optimize the material performance for device applications.

B. PROGRESS

The tungsten bronze $\text{Sr}_{1-x}\text{Ba}_x\text{Nb}_2\text{O}_6$ solid solution, $0.75 \geq x \geq 0.25$, is important for various device applications, specifically electro-optic and photorefractive. Since $\text{Sr}_{0.75}\text{Ba}_{0.25}\text{Nb}_2\text{O}_6$ (SBN:75) exhibits electro-optic and pyroelectric coefficients greater than any other ferroelectric crystal, it is important to develop this material for our ongoing work on materials for photorefractive and other applications. The recent developments in the crystal growth area indicate that the growth of optical quality Ce-doped and undoped SBN:75 crystals is possible, and crystals as large as 1 to 1.5 cm in diameter have been successfully grown. Since this composition is not congruent melting, it is rather difficult to grow as compared to the congruent melting SBN:60 composition. It is expected that the development of such large electro-optic response ($r_{33} = 1400 \times 10^{-12}$ m/V) crystals will have a



significant impact on our various device applications, including electro-optic, photorefractive, and millimeter wave. Currently, efforts are under way to establish its photorefractive properties with respect to cerium dopant concentration.

Another important tungsten bronze crystal, $\text{Sr}_{2-x}\text{Ca}_x\text{NaNb}_5\text{O}_{15}$, is being developed for photorefractive and electro-optic applications. This composition is orthorhombic at room temperature and the electro-optic coefficient is estimated to be 1600×10^{-12} m/V. The growth of small crystals has been successful and further efforts are under way to perfect growth techniques to develop optical quality SCNN crystals.

Work has continued on the ionic substitution of Ca^{2+} in tungsten bronze $\text{Sr}_{0.5}\text{Ba}_{0.5}\text{Nb}_2\text{O}_6$ (SBN:50) ceramic material for pyroelectric detector applications. Simultaneous substitution for both Sr^{2+} and Ba^{2+} results in a substantial decrease in the phase transition temperature T_c , decreasing from 128°C to roughly 50°C for 34% Ca^{2+} substitution. This result is consistent with single ion results where it was found that Sr^{2+} substitution resulted in only a slight increase in T_c , whereas substitution for Ba^{2+} resulted in a considerable decrease in the phase transition temperature. The dielectric loss for these compositions remained low, indicating their qualification for transverse pyroelectric detector applications.



C. MAJOR EQUIPMENT

None.

D. CHANGE IN PERSONNEL

None.

E. TRIPS AND VISITS

In January 1986, Dr. R. R. Neurgaonkar met John Neff of DARPA and gave a briefing on the current status of this program and an outline of future work.

In December 1985, Professor L. E. Cross of Penn State University, visited Rockwell for discussions on the DARPA contract and future work was planned.

F. PUBLICATIONS AND PRESENTATIONS

1. R. R. Neurgaonkar and W. K. Cory, "Progress in Photorefractive Tungsten Bronze Materials, J. Opt. Soc. Am., B/3, 274, (1986).
2. L. E. Cross and R. R. Neurgaonkar, "A Phenomenological Analysis of Tetragonal Tungsten Bronze Ferroelectrics," submitted to J. Mat. Science.

G. FUTURE WORK

Continue to establish the optimum cerium concentration needed to improve the photorefractive response time (~ 1 ms). The effort will be extended to grow optical quality SCNN crystals with and without dopants. Initiate the LPE growth work of bronze



Rockwell International

Science Center

SC5441.QTR

Page 4

compositions such as SBN, SKN and PBN for electro-optic applications.

H. FUNDING

Contract Estimated Cost	\$1,155,549
Fixed Fee	<u>\$ 89,758</u>
Total Estimated Contract Price	\$1,245,307
 Current Contract Funding	 \$ 370,000
Less Fee	<u>\$ 26,772</u>
Available Cost	\$ 343,228
 Expenditure through 02/28/86 (Cost)	 \$ 38,641
Balance of Available Funds (Cost)	\$ 304,587
 Balance of Funding Required to Complete Program	 \$ 902,079